

**DESCRIPTION**

Mineral wall coating, made of common lime, easy to apply. Due to its chemical nature, it does not form a film but hardens directly with the substrate. Considering its high alkalinity, it has a greater resistance to mould compared with ordinary paint for interiors.

It is characterized by high water vapour permeability, and ensures dry walls by preventing condensation in environments subjected to high concentrations of steam such as kitchens and bathrooms.

It provides a low dust retention film that is friction-resistant.

**PERFORMANCE DATA**

		Method	Value
Dirt retention	low	UNI 10792	$\Delta L = 3.5$
Wet scrub resistance		ISO 11998	$L_{diff} = 28 \mu$
Water vapour permeability			high
Specific weight		ISO 2811-1	1540–1550 g/l
Drying time		own PF2	recoatable 6-12h; fully 18h
Solid by weight		own PF25	47-51 %

**SHELF LIFE**

1 year minimum, stored in its unopened original can at temperatures between +5°C and +30°C.

**COLOUR RANGE**

White.

As per samples. The colour could vary slightly from one production batch to the next; therefore, it is important to finish the job with the same batch.

**TYPICAL USE**

Ideal for decorating and protecting new structures or structures undergoing maintenance with different compositions (cement, common lime, premixed), concrete, fibrocement, plasterboard, filler skims and old paints

Considering its predominantly mineral nature, it is not advisable to apply the product on top of water paint. The texture effect depends on the manual skill of the applicator and on the quantity applied. For this reason the samples are only indicative. Before doing the job, run some test on a demonstration panel.

**TOOLS**

Stainless steel trowel.

**THINNING**

Ready to use.

**COVERAGE**

2,5-3,3 m<sup>2</sup>/kg per coat

**APPLY**

+5°C +30°C

**COATING SYSTEM**

**Cement-based, gauged mortar and hydraulic lime-based plasters, new pre-mixed**

1. Remove any trace of dust, and stop up any imperfection with *Stucco Light* filler.
2. Skim the substrate with *Venetian* and smooth out its surface.
3. After approx. 12 hours, apply one more layer to level out the surface.
4. After approx. 12 hours, sandpaper the surface. Eliminate any imperfection, remove the dust and apply small quantities of material. Before drying completely, compacting it and polishing it with a steel plasterer's trowel.

**Reinforced concrete, prefabricated concrete structures, plaster skims, filler skims, plasterboard, old layers of synthetic paint**

1A. First apply an undercoat of *Unifix Fine* primer and proceed as per points 2, 3 and 4.

**SPECIFICATION  
ITEM**

Mineral wall coating, made of common lime with glossy smooth skim finish, high water vapour permeability with a consumption rate of 0,7 kg/m<sup>2</sup>

**INSTRUCTIONS**

To carry out the work in a workmanlike fashion, it is important to follow up the instructions for the preparation of the surfaces contained in the CAP Arreghini Books. This technical information is intended as a rough guide. However, because of the enormous variety of media and application conditions, it is essential to check the suitability of the product and its effectiveness by testing on the specific case.. The specification data and technical information have been calculated at +23°C with relative ambient humidity of 65%. In different conditions the data and the time intervals between one operation and the next vary.