

DESCRIPTION

Mineral wall coating for interiors and exteriors, made of common lime, easy to apply. Due to its chemical nature, it does not form a film but hardens with the substrate. Considering its high alkalinity, it has a greater resistance to mould compared with ordinary paint for interiors.

Excellent water vapour permeability, it ensures dry walls by avoiding condensation in environments subjected to high concentrations of steam such as kitchens and bathrooms. Thanks to its excellent filling properties, it can be applied with manual tools by creating a thick coat with a good compact finishing level and antique effect, distinguished by a variety of colour effects and undertones.

It provides a low dust retention film that is friction-resistant.

PERFORMANCE DATA

	Class	Method	Value
	EN13300		
Dirt retention	low	UNI 10792	ΔL = 5
Water vapour permeability		CAP	High
Specific weight		ISO 2811-1	1450–1550 g/l
Drying time		CAP - PF2	recoatable 12h; fully 12h
Solid by weight		CAP - PF25	47-51 %
Granulometry		CAP	MAX 0.7 mm

SHELF LIFE

1 year minimum, stored in its unopened original can at temperatures between +5°C and +30°C.

COLOUR RANGE

As per samples.

The colour could vary slightly from one production batch to the next; it is therefore, important to finish the job with the same batch.

TYPICAL USE

It is ideal for decorating and protecting new structures or structures undergoing maintenance with different compositions (cement, common lime, premixed), concrete, fibrocement, filler skims old paints and in all cases in which is required a product that meets sustainable building criteria.

Considering its prevalently mineral nature, it is not advisable to apply *Marmorino* plaster on water paint.

The texture effect depends on manual skills of the applicator and on the quantity applied. For this reason the samples are only indicative. Before doing the job, run some tests on a demonstration panel.

TOOLS

Stainless steel trowel.

THINNING

Ready to use

COVERAGE

0,7-0,8 m²/kg per coat

APPLY

+5°C +30°C

COATING SYSTEM

Cement-based, gauged mortar and hydraulic lime-based plasters, new pre-mixed

1. Remove any trace of dust, and stop up any imperfection with *Stucco Light* filler.
2. Skim the substrate with *Marmorino* and smooth out its surface.
3. After approx. 12 hours, apply a one more layer to level out the surface.
4. After approx. 12 hours, sandpaper the surface, eliminate any imperfection, remove the dust. Before drying completely, apply small quantities of material, compacting it and polishing it with a steel plasterer's trowel.

Reinforced concrete, prefabricated concrete structures, plaster skims, filler skims, plasterboard, old layers of synthetic paint

- 1A. First apply an undercoat of *Unifix Fine* primer and proceed as per points 2, 3 and 4.

**SPECIFICATION
ITEM
INSTRUCTIONS**

Mineral wall coating, made of common lime with satin smooth skim finishing.

To carry out the work in a proper way, it is strictly needed to follow up the instructions for the preparation of the surfaces contained in the CAP Arreghini Books. This technical information is intended as a rough guide. However, due to the enormous variety of media and application conditions, it is essential to check the suitability of the product and test the effectiveness on a sample. The specification data and technical information have been calculated at +23°C with relative ambient humidity of 65%. In different conditions the data and the time intervals between the two phases of the above reported coating system can vary.