

**SERIES 2311.0800 EPIC LUCIANO – DIRECT DECORATIVE GLOSSY PLASTER**
**Use**

Self-polishing plaster to be applied with a spatula. The peculiarity of its components along with application techniques make it possible to obtain elegant decorations and refined effects on walls or architectural details such as columns or frames. Applicable on several types of wall surfaces such as gypsum, construction plaster or plasterboard suitably prepared.

It is the basic item to obtain the colours listed in the EPIC LUCIANO file using SISTEMA COLORMAKER and COLORMAKER AQUA products.

Given its high viscosity, we recommend you shake the product using a mixer in order to make colouring components uniform.

**General features**

Soft paste product.

Following application the product has the following characteristics:

- Excellent adherence
- It does not smell bad
- High grade of brilliance
- Low grade of dirt retention

**Technical features** (data collected at a temperature of 20 °C)

Specific weight	kg/l	1.73 ± 0.030
Dry residue	%	72 ± 2
Film aspect	gloss	Glossy after polishing
Yield on smooth plaster	sqm/l	3 – 4
Thinner		The product is ready to be used. If necessary, dilute with little water
Dry to the touch	hours	2
Deep drying time	hours	24
Dry to recoat	hours	8-10
Time before smoothing/polishing	hours	12/24

**Application methods**

Preparation of the surface and application stages:

- 1) Brush the surface carefully.
- 2) Insulate with Titancril series 2340.0003 (see datasheet).
- 3) Make the surface smooth and uniform with 2310.0100 RASANTE PER DECORATIVI  
 Or, *to obtain more intense colours*, about 6 hours after using Titancril, apply 1-2 coats of LUCIANO, one 6/8 hours after the other; smooth only the first coat with fine-grit abrasive paper.
- 4) Apply the final coats of LUCIANO with a stainless steel spatula of a suitable size according to the desired effect.
- 5) After 12/24 hours, brush the surface with a suitable spatula or smoother and trimmer pressing as much as to obtain full polishing (chiaroscuro effect).

Store and apply the product at a temperature of at least 5 °C.

Wash tools with water immediately after use.

Remove any dried product stain using Diluente Nitro 9210.0012.

19/02/2015