

CEMENTINO

Description of product

"Powder mixture" of natural lime, hydraulic binders, and marble fillers for wall concrete decorative effects.

Application Field

CEMENTINO should be applied using a Marmorino Polished Plaster Trowel.

Product characteristics

CEMENTINO is a decorative mono layer product for interior concrete imitations supplied in a "grey base" color, applicable with the classical inox trowel. Bericalce supplies a special powder toner color that added to the base color permits to obtain a range of darker greys. The accurate formulation makes the product very smooth and easy to apply. Cementino is made from an hydraulic base, meaning that it begins to harden after contact with water. For this reason, the best workability of the material is achieved in the first 90 minutes after the product is prepared for use. (This can vary depending on the environment, i.e temperature or humidity).

To add an extra layer of protection, you can apply Wax d'Arte (Natural Beeswax).

Technical data
Name Cementino
Composition Lime, hydraulic binders, natural fillers, resins.
Aspect Powder
Color Grey
Dilution Water 47%
Quantity per layer ca. 1.0 - 1.5 m ² /kg
PH 13 in water solution
Vapour permeability SD - 0.04m (DIN 52615)
Water absorption w - 0.3kg / (m ² h0.5) (EN1062-3:2001)
VOC class VOC 0g/l - wall paint and subcategory "L" max .value UE2010 30g/l
Packaging 12 Kg bucket
Storage Store in a dry place with temperature. 5 ° to 30 ° C
Notice We suggest finishing off the applicated surfaces with a layer of "Natural Bee Wax"

Instructions for use

- Make sure that the surface is completely smooth, and that there are no imperfections. Also make sure there are no chemicals on the surface such as oil, stains, or grease, these must be removed.
- Apply (Unifix) Primer before Cementino to ensure the correct durability and adhesion.
- Cementino should be applied using our Stainless-Steel Trowel. The application should be carried out with an ambient temperature between 5° to 35°C. Different decorative tools can be used depending on the desired effect. - Use tools like stiff brushes, scrapers to create interest in the wet plaster. This is best done about 70 minutes after application.
- Use a drill and add water slowly as you mix, then let the material rest for 70 minutes.
- Cementino can be applied on one or two coats, using a Stainless-Steel trowel. To avoid repeated patterns, apply it using irregular movements.
- Once dry we suggest applying one layer of Impera wax to increase dirt resistance. Please note that although the product has a normal drying time according to its thickness, the real hardness is obtained through carbonation which occurs on contact with air. This process can last many months.

Notes

The present technical chart has been written by Bericalce's experts and the indicated technical and scientific information have been tested in our own workshop.

Any responsibility regarding the results is due only to the method and conditions used during application of the product.

These indications are a valid support for testing the quality of the product in each specific case.

Date of issue 01.04.2004