

GIMCYN CHROMA

Product Description

Gimcyn Chroma is an enhanced metallic paint derived from an aluminium base with pearly particles that creates a stunning textured wall finish with a beautiful luxurious sheen. Gimcyn Chroma is the ideal paint for those looking at intense metallic effects, with bold reflectiveness.

Application Instructions

Gimcyn Chroma is ready to use and can be applied on new and old plasters, concrete surfaces, gypsum plasters, plasterboard, MDF, timber and metal surfaces after Gimcyn primer.

It can be applied by sponge, or brush and the effect can be created by brush, sponge. Gimcyn Chroma should not be diluted with water, but in case of extreme heat or suction, it can be diluted by water up to 5%.

Surface Preparation

Make sure the surface is completely dry, dust free and all impurities have been removed. In case of mould, treat the surface with suitable specific products. Brush or remove any efflorescence and old peeling paint or wallpaper. If you are planning to apply Gimcyn Chroma on a dusty, chalky, high-porous area, you should use Atomo (to be applied before Gimcyn Chroma primer). This will help to consolidate the surface! Once the surface has been prepared, you must apply Gimcyn Chroma primer. Dilute Gimcyn Chroma primer with 30% of water (0.5L of primer with 150mL water, or, 1L of primer with 300 mL water), and apply it with a short pile, or mohair roller. Wait for 2 to 4 hours for the primer to get completely dry.

Before applying Gimcyn Chroma, stir the pot, and apply it with an Italian Special Effect Burhs. Once you've applied a half square metre, and the paint has started to settle (approx. 2 mins), the effect can be changed or finalised with a Tobacco sponge. In case you do a "Brush effect", use the Italian Special Effect Brush. The finish will be touch dry within an hour and completely dry after 12 hours. Only a single coat is needed for the effect, but in case it is required, more paint can be put on the surface using a sponge.

Cleaning of Tools

Tools should be cleaned immediately after use with water.

Technical Specifications

1KG of Gimcyn covers approx. 5 sqm depending on the thickness of the application.

Recommendations

Do not apply Gimcyn Chroma if the substrate, air, or product temperature is lower than +5C and higher than +35C, nor under direct sunlight.