

GIMCYN CHROMA

Product Description

Gimcyn Chroma is an enhanced Metallic Paint derived from an aluminum base with pearly particles that creates a stunning textured wall finish with a beautiful luxurious sheen.

Gimcyn Chroma is the ideal paint for those looking at intense Metallic effects, with bold reflectiveness.

Application Instructions

Gimcyn Chroma is ready to use and can be applied on freshly and/or previously plastered walls, concrete surfaces, gypsum plasters, plasterboard, MDF, timber, and metal surfaces after Gimcyn Chroma primer. Please remember that if you want to apply Gimcyn Chroma on a dusty, chalky, or high porous area, you should use Atomo (**to be applied before Gimcyn Chroma primer**). This will help to consolidate the surface.

It can be applied using an Italian Special Effect Brush and a Tobacco sponge. Gimcyn Chroma should not be diluted with water, but in case of extreme heat, or suction, it can be diluted with water by up to 5%.

Surface Preparation

Make sure that the surface is completely dry, dust free and that all impurities have been removed. In case of mould, treat the surface with suitable specific products. Brush, or remove any efflorescence, and old peeling paint, or wallpaper.

Once the surface has been prepared, you must apply Gimcyn Chroma primer. Dilute the primer with 30% water (150mL of water for 0.5L of primer and 300mL of water for 1L of primer), and apply it with a short pile, or mohair roller. Wait 2-4 hours for the primer to dry completely.

Before applying Gimcyn Chroma, stir the pot and apply it using an Italian Special Effect Brush. Once you've applied 0.5 sqm, and the paint has started to settle (approx. 2 minutes), the effect can be changed or finalized with a Tobacco Sponge. In case you do a "Brush Effect", use the Italian Special Effect Brush. The finish will be touch dry within an hour, and completely dry after 12 hours.

Only a single coat is needed to the effect, but in case it is required, more paint can be put on the surface using a Tobacco Sponge.

GIMCYN CHROMA

Cleaning of the Tools

The tools should be cleaned immediately after use with water.

Technical Specifications

1KG of Gimcyn Chroma covers approximately 5 sqm, depending on the thickness of the application.

Recommendations

Do not apply Gimcyn Chroma if the substrate, air, or product temperature is lower than +5C and higher than +35C, not under direct sunlight.